

DURAK 

DURAMATT[®]



00010

17091

16125

17092

15986

17093

17094

15983

17122

17095

17096

15987

15985

16449

15982

17097

17098

17100

17099

17104

17105

17103

17102

17101

17107

17108

17106

17129

16448


17130




16126



16451




17121




17125




17126




17123




17124




17120



13763



16450



17117



15989




17118



17116



17119



17109



17110



17111



15988



17112



17113



16452



17114



17115



15981




15984




17128




17127



16162



00020



Renk Numaraları Endeksi - Index Of Colour

Colon No. Renk No.	Column Sıra	Colon No. Renk No.	Column Sıra	Colon No. Renk No.	Column Sıra	Colon No. Renk No.	Column Sıra
00010	1	16448	2	17101	2	17116	3
00020	4	16449	1	17102	2	17117	3
13763	3	16450	3	17103	2	17118	3
15981	4	16451	3	17104	2	17119	3
15982	1	16452	4	17105	2	17120	3
15983	1	17091	1	17106	2	17121	3
15984	4	17092	1	17107	2	17122	1
15985	1	17093	1	17108	2	17123	3
15986	1	17094	1	17109	4	17124	3
15987	1	17095	1	17110	4	17125	3
15988	4	17096	1	17111	4	17126	3
15989	3	17097	2	17112	4	17127	4
16125	1	17098	2	17113	4	17128	4
16126	3	17099	2	17114	4	17129	2
16162	4	17100	2	17115	4	17130	2



ÜRÜN ÖZELLİKLERİ

DURAK Duramatt®, yüksek ışık haslığına sahip, % 100 mat Polyester nakış ipliğidir. Durak Duramatt®; yapısı, yumuşaklığı ve yüksek renk gücü ile eşsiz bir görünüme sahiptir. Işığa karşı haslıkta çok yüksek bir dayanım gösterir. Kolaylıkla solmaz ve renkler kalıcıdır. Bu nedenle tüm alanlarda kullanılabilir.

BOYAMA TEKNOLOJİSİ

Işığa karşı yüksek renk haslıkları ile renkleri yoğun bir şekilde yansıtan en yüksek boyama teknolojilerine sahip çevre dostu boyar maddeler ve kimyasal maddeler ile boyanmaktadır. Bitim sırasında renklerde ton farkı oluşturmayan ve depolama sırasında değişmeyen kalıcı renkler için özel formüllü lubrikasyon işlemi uygulanmaktadır.

RENK HASLIKLARI

Yıkama Haslığı	ISO 105 C06	4 - 5
Su Haslığı	ISO 105 E01	4 - 5
Sürtünme Haslığı	ISO 105 X12	4 - 5
Kuru Temizleme Haslığı	ISO 105 D01	4 - 5
Klor Haslığı	ISO 105 N01	4 - 5
Işık Haslığı	ISO 105 B02	6 - 8

DEPOLAMA ŞARTLARI

Aşırı sıcak, nem, doğrudan ısı ve güneş ışığı şartlarından uzak depolanmalıdır.



dtex 160
6 x 1500 m
27 gr



PRODUCT PROPERTIES

DURAK Duramatt® is %100 polyester matt embroidery thread which has very high light fastness. Durak Duramatt® has a unique appearance with its structure, softness and high color power. It has high strength against light fastness goes up to 8. It has colorfast property and colors are permanent. Therefore it is available to use in all fields.

USAGE AREAS

Durak Duramatt® has been produced to be used when you need High Light Fastness. This thread is especially used for high altitude performance clothing, sport clothes, children clothing etc.

DYING TECHNOLOGY

It is dyed with colorant and chemicals environment friendly which has got high dye technology reflecting colors intensely by high color fastness against light. Lubrication process with special formula is applied for permanent color and not color tone during storage and finishing process.

COLOUR FASTNESS


Washing fastness	ISO 105 C06	4-5
Water fastness	ISO 105 E01	4-5
Rubbing fastness	ISO 105 X12	4-5
Dry cleaning fastness	ISO 105 D01	4-5
Chlorine fastness	ISO 105 N01	4-5
Light fastness	ISO 105 B02	6-8

STORAGE CONDITIONS

It should be stored keep away from sunlight , direct heating, humidity and over temperature.



dtex 160
6 x 1500 m
27 gr



Sales & Marketing

DURAK Tekstil Pazarlama AS

Phone : +90 212 468 06 00

Fax : +90 212 468 06 99

Istanbul Dünya Ticaret Merkezi

A3 Blok K. 14 No. 430-433

34149 Yeşilköy-Istanbul/TÜRKİYE

www.durak.com - siparis@durak.com.tr

DURAK Poland

Phone : +48 42 640 71 79

Fax : +48 42 653 29 56

DURAK Spain

Phone : +34 96 14 327 33

Fax : +34 96 12 729 61

DURAK Austria

Phone : +43 55 77 62 367

Fax : +43 55 77 86 011

DURAK Shanghai

Phone : +86 021 336 32 458

Fax : +86 021 336 32 459

2011/1

